POWER COUPLER MANUFACTURING AND QUALITY CONTROL AT CPI

S. Einarson, T. Treado[#], Communications & Power Industries, LLC, Beverly, MA 01915, USA

Abstract

CPI has been designing and manufacturing fundamental power couplers for superconducting accelerators for over a dozen years. We have manufactured approximately 200 power couplers of 16 different designs. Power coupler frequencies have ranged from 175 MHz to 3.9 GHz and power levels have ranged from 5 kW to 500 kW average power. We have developed and qualified several key manufacturing processes including a high-RRR copper plating process and a titanium nitride coating process. In addition, we have established uniform quality control and inspection processes which ensure that the power couplers will meet the requirements for the intended use in superconducting accelerators. These processes have been developed. improved and/or qualified in collaboration with colleagues at superconducting accelerator facilities throughout the world. This paper will provide an overview of these critical manufacturing and quality control processes.

POWER COUPLERS BUILT BY CPI

The Beverly Microwave Division of Communications & Power Industries, LLC (CPI) has been fabricating power couplers for superconducting linear accelerators since 2000. Table 1 lists the power couplers built at CPI. Figures 1 and 2 show representative examples.



Figure 1: VWP3032 power coupler for Cornell.



Figure 2: VWP3107 power coupler for AES.

Table 1: Power Couplers Built at	it CPI
----------------------------------	--------

Table 1. Fower Couplers Built at CF1					
CPI Model Number	Accelerator Application	Freq. (MHz)	Peak, Avg. Power (kW)		
VWP	IFMIF Facility	175	200,		
3097	(CEA Saclay) [1]		200		
VWP	Facility for Rare Isotope	322	14,		
3098	Beams (MSU) [2]		14		
VWP	Radio Frequency 402		600,		
3124	Quadrapole (ORNL)		50		
VWP	NSLSII Upgrade	500	500,		
3107	(AES, BNL)		500		
VWP	Energy Recovery Linac	704	500,		
3070	Gun (AES) [3]		500		
VWP 1185/86	Free Electron Laser Injector (AES) [4]	748	350, 350		
VWP 1133	Spallation Neutron Source (SNS) [5]	805	1000, 60		
VWP	Rare Isotope Accelerator	805	1000,		
1162	Prototype (MSU) [6]		10		
VWP 1137, 3049 (TTF3)	Tesla Test Facility and ILC 1300 1100 R&D 7.2 (CNRS Orsay, DESY, Fermi, SLAC) [7]		1100, 7.2		
VWP 1136	Tesla Test Facility 130 (AMAC) [8]		1100, 7.2		
VWP	XFEL	1300	1100,		
3126	(EuXFEL)		7.2		
VWP 3032	Energy Recovery Linac (Cornell, Triumf) [9,10]		75, 75		
VWP 3069	Energy Recovery Linac (Daresbury) [11]	1300	75, 75		
VWP	SRF Accelerator	1300	60,		
3113	(Peking University)		60		
VWP	Energy Recovery Linac	1300	5,		
3108	(Cornell) [12]		5		
VWP 3088	XFEL Third Harmonic Accelerating Cavity (Fermi, DESY) [13]	3900	45, 12.5		

KEY MANUFACTURING PROCESSES

Several key manufacturing processes were developed at CPI for the fabrication of power couplers. We developed a high-RRR electroplating process for copper on stainless steel as well as a process to deposit an anti-multipactor TiN coating on surfaces [14]. The TiN coating process replicated the process developed at DESY.

Both processes have been in nearly-continuous use for over ten years. The high-RRR plating process was originally qualified at CNRS-Orsay 10 years ago. It has been re-qualified 4 more times since then by DESY for TTF3 (VWP3049) and 3.9 GHz (VWP3088) power coupler production runs. The most recent re-qualification of the high-RRR copper plating process occurred in November 2013. The TiN coating was originally qualified 10 years ago at DESY and has been re-qualified twice since then, once at DESY and once at CEA Saclay. Details of the initial qualification are included in [14].

High-RRR copper plating of power coupler components is a particularly challenging process. While specifications vary, there are common requirements for high purity, high cleanliness, good adhesion, and uniform copper plating. Table 2 indicates the typical specifications for high-RRR copper plating. Included in Table 2 are examples of desired copper plating.

QUALITY CONTROL PROCEDURES


CPI makes use of established workmanship acceptance criteria for power couplers. These workmanship standards are a result of our collaborative efforts over the years with experts at DESY, CNRS-Orsay, Fermi Lab, SLAC, Cornell, CEA-Saclay and elsewhere. In-process inspection is done on production power couplers against quality assurance documents that provide some objectivity against what are arguably subjective standards.

The TTF3 couplers (VWP3049) have workmanship acceptance criteria documents for the key assemblies (warm, cold, and waveguide assemblies). Each of these documents detail areas to be visually inspected, with or without magnification. Inspection with a borescope is also required for many features. For the warm assembly 27 areas are highlighted for visual inspection. For the cold assembly there are 20 inspection points. features are included as inspection points on the waveguide assembly. Three conditions are called out for each inspection point. A Target Condition is defined as "a condition close to perfect / preferred, however, it is a desirable condition and not always achievable and may not be necessary to ensure reliability of the assembly in its service environment". An Acceptable Condition is defined as "a condition that, while not necessarily perfect, will maintain the integrity and reliability of the assembly in its service environment." A Defect Condition is defined as "a condition that may be insufficient to ensure the form, fit, or function of the assembly in its end use environment."

Table 2: Copper Plating Specifications and Examples

Require- ment	Typical Specifica- tion	Example of Desired Result
Thickness uniformity	± 30%	$\int \int \int$

Surface 32 microfinish inch finish



Microthickness uniformity No concavities



Cleanliness, oxide free



RRR value 30 - 80

The acceptance documents have been populated with photographs of Target Conditions, Acceptable Conditions, and Defect Conditions as these conditions are identified. Currently these documents are works-in-progress and will be updated for the VWP3126 production program for the EuXFEL.

Figure 3 shows an example of one critical feature in the VWP3049 cold assembly (e-beam weld) and the photos in the associated workmanship standard. A sample borescope photo of the Target Condition for the e-beam weld


is shown at the top of Figure 3. The bottom two borescope photos in Figure 3 show Acceptable Conditions. There is no depression in the Target Condition weld while a slight depression is evident in the Acceptable Condition welds. Some minor scratches are seen in the photos of the Acceptable Conditions. We have no examples of the Defect Condition for this feature at this time.

ONGOING ACTIVITIES


CPI is currently expanding its power coupler manufacturing capabilities by adding an ISO 4 – ISO 6 clean room for cleaning and final assembly of power couplers. This clean room is being built to support production at a rate of up to 8 power couplers per week.

Area (16) Weld: internal form, irregularities, penetration


Target: E-beam Weld



Acceptable: E-beam Weld



Acceptable: E-beam Weld



Defect: *Ebeam* No weld material visible.

Figure 3: Example from CPI workmanship standard.

CONCLUSION

CPI has successfully manufactured 200 power couplers over the last 12 years of 16 different designs. We have established and qualified several key manufacturing and quality control processes that have been refined during several production programs and are in current use.

REFERENCES

- [1] H. Jenhani, P. Bosland, P. Carbonnier, N. Gouas, P. Hardy, V. Hennion, F. Orsini, J. Plouin, B. Renard, S. Einarson, and T. Treado, "Input Power Coupler for the IFMIF SRF Linac," Proc. IPAC2012, New Orleans, 2012.
- [2] J. Popielarski, et al. "Development and Testing of Prototype Fundamental Power Couplers for FRIB Half Wave Resonators," Proc. SRF2011, Chicago, IL, 2011.
- [3] W. Xu et al. "Conditioning the Fundamental Power Coupler for ERL SRF Gun", Proc. SRF2011, Chicago IL, 2011.
- [4] A. Todd et al. "High-current accelerator development for FELS and ERLs", Proc. PAC07, Albuquerque, NM, 2007.
- [5] Q.S. Shu, J. Susta, G. Cheng, S. Einarson, T. Treado, W. Guss, and M. Tracy, "Design, Fabrication, and Testing of Novel High Power RF Input Couplers," High Power Coupler Workshop, Newport News, 2002.
- [6] Q.S. Shu, J. Susta, G. Cheng, T. Grimm, J. Popielarski, S. Einarson, and T. Treado, "Design and Fabrication of Input RF Coupler Windows for the U.S. Rare Isotope Accelerator Project (RIA)," Proc. SRF2003, Hamburg, Germany, 2003.
- [7] T. Garvey, "CW and Pulsed Power Couplers Design and Performance Review," Proc. SRF2005, Ithaca, NY, 2005.
- [8] Q.S. Shu, J. Susta, G. Cheng, T. Treado, S. Einarson, D. Proch, W.D. Moeller, and T. Garvey, "High Power Coupler for the Tesla Superstructure Cavities," Proc. PAC05, Knoxville, 2005.
- [9] V. Veshcherevich, etal, "Design of High Power Input Coupler for Cornell ERL Injector Cavities," Proc. SRF2005, Ithaca, NY, 2005.
- [10] A.K. Mitra et al. "High Power Coupler Test for Triumf E-linac SC Cavities," Proc. of LINAC 2012, Tel-Aviv, Israel, 2012.
- [11] A. Wheelhouse et al, "Daresbury International Cryomodule Coupler Progress," Proc. IPAC 2010, Kyoto, Japan, 2010.
- [12] V. Veshcherivich and S. Belomestynkh, "Input Coupler for Main Linac of Cornell ERL," Proc. SRF2013, Paris, France, 2013.
- [13] N. Solyak, "Cavity and Coupler Design," 3rd Harmonic Cavity Review," Nov. 2005, http://ilcdms.fnal.gov/Workgroups/3.9%20GHz%20SCRF %20Program%20Review/.
- [14] T. Treado and S. Einarson, "Power Couplers for the ILC," Proc. PAC07, Albuquerque, NM, 2007.